

WHAT IS CLAIMED IS:

Sub
A1
5 1. A fire-retardant antistatic vinyl chloride resin molding, which comprises a base layer comprising a vinyl chloride resin and an antistatic layer comprising a conductive material and being laminated on at least one side of said base layer, wherein the base layer comprises from 5 to 50 parts by weight of a titanium compound and 100 parts by weight of a vinyl chloride resin.

10 2. A fire-retardant antistatic vinyl chloride resin molding, which comprises a base layer comprising a vinyl chloride resin and an antistatic layer comprising a conductive material and being laminated on at least one side of said base layer, wherein said base layer comprises a vinyl chloride resin having a chlorination degree of from
15 58 to 73%.

20 3. A fire-retardant antistatic vinyl chloride resin molding, which comprises a base layer comprising a vinyl chloride resin and an antistatic layer comprising a conductive material and being laminated on at least one side of said base layer, wherein said base layer comprises 100 parts by weight of a vinyl chloride resin having a chlorination degree of less than 58% and at least one of
25 (a) from 0.5 to 15 parts by weight of a phosphorus fire-retarding agent and (b) from 0.5 to 20 parts by weight of chlorinated polyethylene.

Sub
A1

4. A fire-retardant antistatic vinyl chloride resin molding, which comprises a base layer comprising a vinyl chloride resin and an antistatic layer comprising a conductive material and being laminated on at least one side of said base layer, wherein said base layer comprises 100 parts by weight of a vinyl chloride resin having a chlorination degree of less than 58% and from 0.1 to 2.5 parts by weight of a molybdenum compound.

5. A fire-retardant antistatic vinyl chloride resin molding, which comprises a base layer comprising a vinyl chloride resin and an antistatic layer comprising a conductive material and being laminated on at least one side of said base layer, wherein said base layer comprises 100 parts by weight of a vinyl chloride resin having a chlorination degree of less than 58% and from 0.0005 to 10 parts by weight of at least one of a foaming agent, a decomposition accelerator agent, a radical generator agent and a cross-linking agent.

6. The antistatic vinyl chloride resin molding according to any one of claims 1 to 5, which further comprises an intermediate layer of a vinyl chloride resin having a different composition from that of the base layer, between the base layer and the antistatic layer.

7. The antistatic vinyl chloride resin molding according to claim 6, wherein said intermediate layer

comprises 100 parts by weight of a vinyl chloride resin and from 2 to 30 parts by weight of a titanium compound.

8. The antistatic vinyl chloride resin molding according to claim 6, wherein said intermediate layer
5 comprises a vinyl chloride resin having a chlorination degree of from 58 to 73%.

9. The antistatic vinyl chloride resin molding according to claim 6, wherein the intermediate layer has a thickness of 200 μ m or less and comprises a vinyl chloride
10 resin having a chlorination degree of less than 58%.

10. The antistatic vinyl chloride resin molding according to claim 6, wherein the intermediate layer comprises 100 parts by weight of a vinyl chloride resin having a chlorination degree of less than 58% and at least
15 one of (a) from 0.5 to 15 parts by weight of a phosphorus fire-retarding agent and (b) from 0.5 to 20 parts by weight of chlorinated polyethylene.

11. The antistatic vinyl chloride resin molding according to claim 6, wherein the intermediate layer
20 comprises 100 parts by weight of a vinyl chloride resin having a chlorination degree of less than 58% and from 0.1 to 2.5 parts by weight of a molybdenum compound.

12. The antistatic vinyl chloride resin molding according to claim 6, wherein the intermediate layer
25 comprises 100 parts by weight of a vinyl chloride resin having a chlorination degree of less than 58% and from

0.0005 to 10 parts by weight of at least one of a foaming agent, a decomposition accelerator agent, a radical generator agent and a cross-linking agent.

5 13. The antistatic vinyl chloride resin molding according to any one of claims 1 to 5, wherein the antistatic layer comprises, as a binder resin, a vinyl chloride resin having a chlorination degree of from 58 to 73%, and a conductive material.

10 14. The antistatic vinyl chloride resin molding according to any one of claims 1 to 5, wherein the antistatic layer comprises, as a binder resin, a ultraviolet curing or thermosetting resin, and a conductive material.

15 15. The antistatic vinyl chloride resin molding according to any one of claims 1 to 5, wherein the conductive material is at least one of tin oxide, a conductive titanium oxide, and a twisting and entangling ultra thin long carbon fiber.

TOP SECRET